

One-stop PURCHASE

Perfect price-performance ratio products

Professional SERVICE



Many types of solid materials must be ground or milled into finer particles for dispersion in appropriate liquid vehicles. The physical properties of the resulting dispersions, often called "grinds", depend not only on the actual size of the individual particles, but also on the degree to which they are dispersed.

The Fineness Gauges are used to indicate the fineness of grind or the presence of coarse particles or agglomerates in a dispersion. It does not determine particle size or particle size distribution.

Grind gauges are used in controlling the production, storage, and application of dispersion products produced by milling in the paint, plastic, pigment, printing ink, paper, ceramic, pharmaceutical, food and many other industries.

The Fineness Gauges is a flat steel block in the surface of which are one or two flat-bottomed grooves varying uniformly in depth from a maximum at one end of the block to zero near the other end. Groove depth is graduated on the block according to one or more scales used for measuring particle size.

The degree of dispersion is indicated in Microns or "Hegman" . The Hegman scale ranges from 0 to 8 with numbers increasing as the particle size decreases.

0 Hegman =100 microns particle size

4 Hegman =50 microns particle size

8 Hegman = 0 microns particle size

The gauge and its scraper are made of hardened stainless steel and have one or two grooves with a graded slope (dependent on the model chosen), graduated in microns, mils, NS (Hegman), the gauges have a tolerance of $\pm 2 \mu$ m

It comfirms the below standards: ISO 1524, ASTM D 3333, ASTM D 1210, ASTM D 1316, DIN En21524

Procedure

Place a slight excess of sample in the deep end of the groove, and with the straight-edge scraper provided, draw the sample toward the shallow end of the groove. Ratings are in term of the point on the scale where the oversize particles, or furrows made by them, first appear in substantial concentration.



Description	Order In formation	Groove Size (L×W)	Ranges	Overall dimension	Graduation	Number of Grooves
Single-Channel Grind Gauge	BGD 241/1	140 × 12.5mm	0-25um	$170 \times 50 \times 12$ mm	1.25um	1
	BGD 241/2	140 × 12.5mm	0-50um	170 × 50 × 12mm	2.5um	1,00
	BGD 241/3	140 × 12.5mm	0-100um	170 × 50 × 12mm	5um	Ø 1
Double-Channel Grind Gauge	BGD 242/1	140 × 12.5mm	0-25um	170 × 65 × 12mm	1.25um	ò 2
	BGD 242/2	140 × 12.5mm	0-50um	170 × 65 × 12mm	2.5um	2
	BGD 242/3	140 × 12.5mm	0-100um	170 × 65 × 12mm	5um	2
Wide-Channel Grind Gauge	BGD 244/1	140 × 37mm	0-25um	170 × 65 × 12mm	1.25um	7 1 🕸
	BGD 244/2	140 × 37mm	0-50um	170 × 65 × 12mm	2.5um	<u></u> <u>8</u>
	BGD 244/3	140 × 37mm	0-100um	170 × 65 × 12mm	5um	Giug 1
		76.5	1.77.7	01		- V